

Product Description

MetecnoPanel[®] is a durable, insulated wall and ceiling panel with a PIR (Polyisocyanurate) fire-retardant core and high performing thermal properties. MetecnoPanel[®] is FM Approved to FM 4880 & 4881 - No Height Restriction and is recommended where improved fire performance is required for insurance purposes. MetecnoPanel[®] is available in a variety of panel surface profiles and COLORBOND[®] colours to create an inspiring interior and exterior finish.

Panel Properties						
Panel Thickness (mm)	50	75	100	125	150	200
Typical Mass (kg/m ²) based on 0.6/0.6mm skins	12.0	13.0	14.0	14.7	15.5	17.4
Declared λ (W/m.K) at 23°C	0.023	0.023	0.023	0.023	0.023	0.023
Declared R-value (m ² K/W) at 23°C (AU)	2.20	3.30	4.45	5.55	6.65	8.90
Total R-value (m ² K/W) at 6°C	2.61	3.84	5.06	6.29	7.51	9.96
Total R-value (m ² K/W) at 15°C (Winter)	2.49	3.66	4.83	5.99	7.16	9.49
Total R-value (m ² K/W) at 30°C (Summer)	2.31	3.38	4.46	5.53	6.60	8.75

Note: The Declared R-value is at 23°C in accordance with AS/NZS 4859.1:2018 & AS/NZS 4859.2:2018.

Span Table

NON-CYCLONIC REGION A&B (WALL APPLICATIONS ONLY)

PIR Core / 0.6mm Steel Skins.

Maximum uniformly distributed ultimate wind load (kPa) for the given span:

Single Span - wind pressure acting inwards/outwards						
Span (mm)	Panel Thickness (mm)					
	50	75	100	125	150	200
1500	2.93	4.39	5.86	7.32	8.79	11.72
2700	1.63	2.44	3.25	4.07	4.88	6.51
3900	1.10	1.65	2.20	2.74	3.29	4.39
5100	0.64	0.96	1.28	1.60	1.93	2.57
6300	0.37	0.63	0.84	1.05	1.26	1.68
7500	0.23	0.45	0.59	0.74	0.89	1.19

Multi Span - wind pressure acting inwards/outwards						
Span (mm)	Panel Thickness (mm)					
	50	75	100	125	150	200
1500	3.91	5.86	7.81	9.33	11.72	11.93
2700	2.17	3.25	4.34	5.18	6.51	6.63
3900	1.10	1.65	2.20	2.74	3.29	4.39
5100	0.64	0.96	1.28	1.60	1.93	2.57
6300	0.42	0.63	0.84	1.05	1.26	1.68
7500	0.30	0.45	0.59	0.74	0.89	1.19



Core	PIR (Fire-retardant Polyisocyanurate)
Width (cover mm)	1100, 1200 (available upon request)
Thickness (mm)	50, 75, 100, 125, 150, 200
Length	Up to 25m (check for availability)
External Material	BlueScope [®] Steel 0.5mm, 0.6mm G300; Grade 316 Stainless Steel 0.55mm
External Finishes	Plain, Finline, Satinline, Ribbed
Exterior Colour Options	Surfmist [®] . Other colours available subject to minimum order quantities.
Internal Material	BlueScope [®] Steel 0.5mm, 0.6mm G300; Grade 316 Stainless Steel 0.55mm
Internal Finishes	Plain, Finline, Satinline, Ribbed
Interior Colour Options	COLORBOND [®] Intramax [™]
Paint System	AS/NZS 2728 & AS 1397
Acoustic Properties	Rw 25 - 27 depending on thickness
Material Group Numbers	C1.10 Group 2 ^a
Bushfire Attack Level	BAL-40 200mm: BAL-FZ (All exposed core to be covered with flashing)
FM Approval	4880, 4881
Environmental	Zero Ozone Depleting Potential (ODP)
Fire hazard properties	AS/NZS 1530.3
Ignitability Index	0
Spread of Flame Index	0
Heat Evolved Index	0
Smoke Index	4
SMOGR _{HC}	< 100


a. AS 5637.1 / AS ISO 9705 - BCA Group Number (Spec C1.10)
MetecnoPanel[®] PIR steel skinned insulated building panels conform to the requirements of the BCA Specification C1.10 Group 2.
Group 2
Panel up to 200mm thick with aluminium 'wall-wall' and 'wall-ceiling' angles (1.5mm) fixed with aluminium rivets or screws is classified as Group 2. Panel up to 200mm with steel 'wall-wall' and 'wall-ceiling' angles (0.5mm) fixed with steel rivets or screws is classified as Group 2.

The technical information contained in this document cover a breadth of applications where MetecnoPanel[®] may be used, which may be outside the scope of our CodeMark certificate. Data specific to CodeMark certification can be found on MetecnoPanel[®]'s CoC CM40196.


SPAN TABLE NOTES:

- Extended span tables including cyclonic regions C&D are also available. Refer Metecno[®].
- Fixing with min. 14g tek screws (x4 off) or mushroom head bolts (x2 off) per fixing point are required.
- Pressures specified are for wind gusts only per AS/NZS 1170.2.
- Deflection limit of span/150 applies, and in accordance with Serviceability Limit State criteria per AS/NZS 1170.0 - TABLE C1. Metecno[®] tests comply with details outlined in AS 4040.0, AS 4040.1, AS 4040.2, AS 4040.3, AS 1562.1 and AS/NZS 1170.1.


Joint



Profiles



Dimensions



Bondor[®] National Network

BRISBANE / EXPORT
103 Ingram Road
Acacia Ridge QLD 3029
T: 07 3323 8500
F: 07 3323 8501

PERTH
17 Gauge Circuit
Canning Vale WA 6155
T: 08 9256 0600
F: 08 9256 0620

MELBOURNE
6 Dunmore Drive
Truganina VIC 3029
T: 03 8326 8000
F: 03 8326 8099

ADELAIDE
70 - 72 Rundle Road
Salisbury South SA 5106
T: 08 8282 5000
F: 08 8282 5099

SYDNEY
49 - 53 Newton Road
Wetherill Park NSW 2164
T: 02 9609 0888
F: 02 9729 1114

LAUNCESTON
7 Connector Park Drive
Kings Meadows TAS 7249
T: 03 6335 8500
F: 03 6335 8544

To connect to your nearest Bondor[®] branch simply call 1300 300 099 or visit www.bondor.com.au

Metecno Pty Limited. ABN 44 096 402 934. The manufacturer reserves the right to change the specification without notice. Bondor[®], Equitill[®], BondorPanel[®], FlameGuard[®], FlameGuard[®] Plus, MetecnoPanel[®], MetecnoInspire[®], EconoClad[®], MetecnoKasset[®], MetecnoTherm[®], InsulWall[®], LuxeWall[®], DesignerWall[®], SolarSpan[®], InsulRoof[®], MetecnoSpan[®], CoolRoof[®], Equideck[®], InsulLiving[®], Metecno[®] are trademarks of Metecno Pty Limited. BlueScope, COLORBOND[®], Intramax[™] and colour names are trademarks of BlueScope Steel Limited. The colours shown in this publication have been reproduced to represent actual product colours as accurately as possible. However, given printing limitations, we recommend checking your chosen colour against an actual sample before placing orders. This advice is of a general nature only. Designers must provide for adequate structural performance and other Building Code requirements. *Conditions may apply. **Limited availability, minimum order quantity may be required. ^Check with NCC for permissible Solar Absorptance before selecting the exterior roof colour. Darker colours may be warranted for use in limited regions refer to www.bondor.com.au as this information is subject to change. Consult Bondor[®] for your application. BON0126 Tech Data Sheets - MetecnoPanel v55 23/07/2021



Leaders in Thermal & Architectural Building Solutions