

Product Description

BondorPanel[®] is a versatile and high performing insulated wall and ceiling panel used in controlled environments such as cold storage, food preparation areas and clean rooms, but extends its use to transportable offices, wall partitions and many other applications.

Panel Properties							
Panel Thickness (mm)	50	75	100	125	150	200	250
Typical Mass (kg/m²)	11.3	11.6	12.0	12.3	12.7	13.3	14.0
SL Grade Declared λ (W/m.K) at 23°C	0.042	0.042	0.042	0.042	0.042	0.042	0.042
SL Grade Declared R-value (m²K/W) at 23°C	1.20	1.80	2.40	3.00	3.60	4.85	6.05
SL Grade Total R-value (m²K/W) at 6°C	1.45	2.10	2.74	3.38	4.03	5.31	6.60
SL Grade Total R-value (m²K/W) at 15°C (Winter)	1.41	2.04	2.66	3.28	3.91	5.16	6.41
SL Grade Total R-value (m²K/W) at 30°C (Summer)	1.34	1.94	2.53	3.13	3.72	4.91	6.09
Note: The Declared R-value is at 23°C in accordance with AS/NZS 4859.1:2018 & AS/NZS 4859.2:2018.							

Span Table

NON-CYCLONIC REGION A&B (WALL APPLICATIONS ONLY)
SL Grade EPS-FR Core / 0.6mm Steel Skins.
Maximum uniformly distributed ultimate wind load (kPa) for the given span:

Single Span, wind pressure acting outwards							
Span (mm)	Panel Thickness (mm)						
	50	75	100	125	150	200	250
1500	3.39	5.09	6.79	8.48	10.18	13.58	16.97
2700	1.86	2.83	3.77	4.71	5.66	7.54	9.43
3900	0.95	1.57	2.09	2.62	3.14	4.19	5.24
5100	0.54	0.92	1.22	1.53	1.84	2.45	3.06
6300	0.33	0.60	0.80	1.00	1.20	1.60	2.01
7500	-	0.42	0.57	0.71	0.85	1.13	1.42
8700	-	0.30	0.42	0.53	0.63	0.84	1.05

Multi Span, wind pressure acting outwards							
Span (mm)	Panel Thickness (mm)						
	50	75	100	125	150	200	250
1500	2.72	4.07	5.43	6.79	8.15	9.92	9.92
2700	1.51	2.26	3.02	3.77	4.53	5.51	5.51
3900	1.04	1.57	2.09	2.61	3.13	3.82	3.82
5100	0.61	0.92	1.22	1.53	1.84	2.45	2.92
6300	0.40	0.60	0.80	1.00	1.20	1.60	2.01
7500	0.28	0.42	0.57	0.71	0.85	1.13	1.42
8700	-	0.32	0.42	0.53	0.63	0.84	1.05

*Refer notes 1-4.

Span Table Internal Cold Storage

SL Grade EPS-FR Core / 0.6mm Steel Skins. Maximum span (mm):

Single Span, internal cold storage 0°C or more							
Span (mm)	Panel Thickness (mm)						
	50	75	100	125	150	200	250
Walls (Non-Load Bearing)	-	5700	7100	8300	9300	10800	12000
Walls (Load Bearing)	-	5100	6500	7500	8200	9500	10700
Ceilings	-	5100	6300	7200	7800	9000	9900

Multi-span, internal cold storage 0°C or more							
Span (mm)	Panel Thickness (mm)						
	50	75	100	125	150	200	250
Walls (Non-Load Bearing)	-	6500	7500	8900	9100	10500	11700
Walls (Load Bearing)	-	6000	6900	7700	8400	9700	10900
Ceilings	-	5300	6000	6900	7500	8600	9600

*Refer notes 3-10.



Core	EPS-FR (Expanded Polystyrene with fire retardant)
Width (cover mm)	1200
Thickness (mm)	50, 75, 100, 125, 150, 200, 250
Length	Up to 16m (check for availability)
External Material	BlueScope COLORBOND [®] Steel 0.6mm G300 CRP Grade
External Finishes	Plain, Ribbed, Satinline
Exterior Colour Options	COLORBOND [®] Intramax [™] or other standard & non-standard colours
Internal Material	BlueScope Colorbond [®] Steel 0.6mm G300 CRP Grade
Internal Finishes	Plain
Interior Colour Options	COLORBOND [®] Intramax [™]
Paint System	AS/NZS 2728 & AS 1397
Acoustic Properties	Rw 24 - 25 depending on thickness
Material Group Numbers	C1.10 Group 1 & 2 ^a
Bushfire Attack Level	BAL-40 (All exposed core to be covered with flashing)
Fire Hazard Properties	AS/NZS 1530.3
Ignitability Index	0
Spread of Flame Index	0
Heat Evolved Index	0
Smoke Index	2-3
SMOGR _{RC}	< 100


a. AS 5637.1 / AS ISO 9705 - BCA Group Number (Spec C1.10)
BondorPanel[®] EPS-FR steel skinned insulated building panels conform to the requirements of the BCA Specification C1.10 as either Group 2 or Group 1 depending on panel thickness and construction details. Refer Bondor[®] for more information.

The technical information contained in this document cover a breadth of applications where BondorPanel[®] may be used, which may be outside the scope of our Codemark certificate. Data specific to CodeMark certification can be found on BondorPanel[®]'s CoC CM40189.


SPAN TABLE NOTES:

- Extended span tables including cyclonic regions C&D and 300mm thick panel are also available. Refer Bondor[®].
- Fixing with min. 14g tek screws (x4 off) or mushroom head bolts (x2 off) per fixing point are required.
- Pressures specified are for wind gusts only per AS/NZS 1170.2.
- Deflection limit of span/150 applies, and in accordance with Serviceability Limit State criteria per AS/NZS 1170.0 - TABLE C1.
- This span table applies for cold storage constructed wholly within a larger enclosed building. Pressure relief port is to be provided for a freezer in accordance with Bondor[®] recommendation.
- Panel thicknesses of not less than 100mm are recommended for chillers, not less than 150mm for freezers and not less than 200mm for blast freezers, depending on structural considerations. Check 'R' value for insulation requirements.
- Fixing with mushroom head bolts (x1 off) minimum per panel per line of support is required.
- Self weight of the panel has been allowed for, plus an allowance of up to 10kg/m² for light duty fittings (lights, etc.). No other dead loads permitted.
- Non-trafficable maintenance access (concentrated load) of 140kg on any span has been allowed for.
- Distributed live load of 0.25kPa (as per AS/NZS 1170.1) has been allowed for. Bondor[®] tests comply with details outlined in AS 4040.0, AS 4040.1, AS 4040.2, AS 4040.3, AS 1562.1 and AS/ NZS 1170.1.



Joint



Profiles



Dimensions



Bondor [®] National Network		
BRISBANE / EXPORT 103 Ingram Road Acacia Ridge QLD 4110 T: 07 3323 8500 F: 07 3323 8501	MELBOURNE 6 Dunmore Drive Truganina VIC 3029 T: 03 8326 8000 F: 03 8326 8099	SYDNEY 49 – 53 Newton Road Wetherill Park NSW 2164 T: 02 9609 0888 F: 02 9729 1114
PERTH 17 Gauge Circuit Canning Vale WA 6155 T: 08 9256 0600 F: 08 9256 0620	ADELAIDE 70 – 72 Rundle Road Salisbury South SA 5106 T: 08 8282 5000 F: 08 8282 5099	LAUNCESTON 7 Connector Park Drive Kings Meadows TAS 7249 T: 03 6335 8500 F: 03 6335 8544
To connect to your nearest Bondor [®] branch simply call 1300 300 099 or visit www.bondor.com.au		

Metecno Pty Limited. ABN 44 096 402 934. The manufacturer reserves the right to change the specification without notice. Bondor[®], Equitilt[®], BondorPanel[®], FlameGuard[®], MetecnoPanel[®], EconoClad[®], MetecnoKasset[®], InsulWall[®], LuxeWall[®], DesignerWall[®], SolarSpan[®], InsulRoo[®], MetecnoSpan[®], Purline[®], Equideck[®], InsulLiving[®], Metecno are trademarks of Metecno Pty Limited. BlueScope, COLORBOND[®] Intramax[™] and colour names are trademarks of BlueScope Steel Limited. The colours shown in this publication have been reproduced to represent actual product colours as accurately as possible. However, given printing limitations, we recommend checking your chosen colour against an actual sample before placing orders. This advice is of a general nature only. Designers must provide for adequate structural performance and other Building Code requirements. This information is subject to change. Refer to Bondor[®] website for latest version. Consult Bondor[®] for your application. BON0126 Tech Data Sheets - BondorPanel v51 29/08/2022



Leaders in Thermal & Architectural Building Solutions